

Battery For General Use 12V/7.2A

TLBAT127



Applications

- ♦ All purpose
- ♦ Uninterruptable Power Supply (UPS)
- ♦ Electric Power System (EPS)
- ♦ Emergency backup power supply
- ♦ Emergency light
- ♦ Railway signal
- ♦ Aircraft signal
- ♦ Alarm and security system
- ♦ Electronic apparatus and equipment
- ♦ Communication power supply
- ♦ DC power supply
- ♦ Auto controlsystem

Specification

Nominal Voltage	12V	
Nominal Capacity(20HR)	7.2AH	
Dimension	Length	151±1mm (5.95 inches)
	Width	65±1mm (2.56 inches)
	Container Height	94.5±1mm (3.72inches)
	Total Height (with Terminal)	99±1mm (3.9 inches)
Approx Weight	Approx 2.00 kg(±0.03kg)	
Terminal	T1 / T2	
Container Material	ABS	
Rated Capacity	7.20 AH/0.350A	(20hr ,1.80V/cell,25°C/77°F)
	6.51 AH/0.651A	(10hr,1.80V/cell,25°C/77°F)
	5.95 AH/1.19A	(5hr,1.75V/cell,25°C/77°F)
	5.37 AH/1.79A	(3hr,1.75V/cell,25°C/77°F)
	4.40 AH/4.40A	(1hr,1.60V/cell,25°C/77°F)
Max. Discharge Current	105A (5s)	
Internal Resistance	Approx 23mΩ	
Operating Temp.Range	Discharge : -15 ~50°C (5 ~122°F)	
	Charge : 0 ~40°C (32 ~104°F)	
	Storage : -15 ~40°C (5 ~104°F)	
Nominal Operating Temp. Range	25 ±3°C (77 ±5°F)	
Cycle Use	Initial Charging Current less than2.16A.Voltage	
	14.4V~14.9V at 25°C(77°F)Temp. Coefficient -30mV/°C	
Standby Use	No limit on Initial Charging Current Voltage	
	13.5V~13.8V at 25°C(77°F)Temp. Coefficient -20mV/°C	
Capacity affected by	40°C (104 °F)	103%
Temperature	25°C (77 °F)	100%
	0°C (32 °F)	86%
Self Discharge	Techfine batteries may be stored for up to 6months at 25°C(77°F)and then a freshening charge is required. For higher temperatures the time interval will be shorter.	

(°FConstant Current Discharge (Amperes) at 25 °C(77


F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	13.3	10.2	8.48	7.33	5.67	4.18	3.52	2.08	1.63	1.32	1.08	0.94	0.756	0.631	0.347
1.80V/cell	17.9	13.1	10.2	8.67	6.69	4.86	3.94	2.27	1.75	1.41	1.16	1.01	0.802	0.651	0.350
1.75V/cell	20.2	14.4	11.2	9.32	6.94	5.04	4.13	2.36	1.79	1.45	1.19	1.03	0.816	0.669	0.354
1.70V/cell	22.2	15.7	11.9	9.80	7.23	5.24	4.26	2.42	1.83	1.48	1.22	1.05	0.827	0.682	0.360
1.65V/cell	24.5	16.9	12.7	10.4	7.63	5.37	4.35	2.45	1.91	1.54	1.25	1.08	0.840	0.696	0.365
1.60V/cell	27.0	18.4	13.6	11.1	8.05	5.60	4.40	2.56	1.97	1.58	1.30	1.10	0.848	0.704	0.367

(°F) Constant Power Discharge (Watts) at 25 °C (77


F.V/Time	5min	10min	15min	20min	30min	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	24.4	18.9	15.8	13.8	10.8	8.03	6.79	4.04	3.18	2.59	2.12	1.84	1.492	1.250	0.686
1.80V/cell	32.4	23.9	18.9	16.1	12.6	9.26	7.57	4.38	3.40	2.75	2.26	1.97	1.578	1.286	0.692
1.75V/cell	35.7	25.8	20.3	17.2	12.9	9.52	7.88	4.53	3.45	2.80	2.31	2.02	1.602	1.319	0.698
1.70V/cell	38.2	27.5	21.4	17.9	13.4	9.86	8.10	4.63	3.54	2.87	2.37	2.05	1.622	1.345	0.710
1.65V/cell	41.6	29.4	22.6	18.9	14.0	10.0	8.23	4.67	3.67	2.96	2.43	2.09	1.644	1.370	0.719
1.60V/cell	44.8	31.2	23.8	19.9	14.7	10.4	8.26	4.85	3.76	3.04	2.50	2.13	1.656	1.383	0.722

Note The above data are average values, and can be obtained with 3 charge/discharge cycles. These are not minimum values.


Dimensions




Float Charging Characteristics




Discharge Characteristics



Temperature Effects in Relation to Battery Capacity



Effect of Temperature on Long Term Float Life



Cycle Life in Relation to Depth of Discharge

Self Discharge Characteristics